

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 837 459 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
22.04.1998 Bulletin 1998/17

(51) Int. Cl.⁶: G11B 7/24, C09B 67/00,
C09B 50/00

(21) Application number: 97203048.0

(22) Date of filing: 04.10.1997

(84) Designated Contracting States:
AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE
Designated Extension States:
AL LT LV RO SI

(30) Priority: 16.10.1996 US 734432

(71) Applicant: EASTMAN KODAK COMPANY
Rochester, New York 14650 (US)

(72) Inventors:
• Chapman, Derek David,
Eastman Kodak Company
Rochester, New York 14650-2201 (US)

• Cunningham, Michael Paul,
Eastman Kodak Company
Rochester, New York 14650-2201 (US)
• Goswami, Ramanuj,
Eastman Kodak Company
Rochester, New York 14650-2201 (US)
• Fleming, James C.,
Eastman Kodak Company
Rochester, New York 14650-2201 (US)

(74) Representative:
Nunney, Ronald Frederick Adolphe et al
Kodak Limited,
Patent Departement (W92)-3A,
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(54) Optical recording elements having recording layers containing mixtures of no K metallized formazan and cyanine dyes

(57) An optical recording element is disclosed. The element has a transparent substrate and on the surface of said substrate, a recording layer and a light reflecting layer wherein recording layer comprises a mixture of a metallized formazan dye and cyanine dye and the unrecorded layer is such that the real part of the refractive index(n) at 780 nm is greater than 1.8 and the imaginary part (k) is less than 0.15. The metallized formazan dye has a k value of 0.00 to 0.02.

EP 0 837 459 A1

Description

Field of the Invention

The present invention relates to optical recording elements, including optical recordable compact disks.

Background of the Invention

There are many known types of optical recording elements. One of the currently popular elements is the compact disk (CD). Digital information is stored in the form of high optical density marks or pits on an otherwise reflective background. In this format, the optical information is most often in the form of read only memory or ROM. Optical information is not usually recorded in real time but rather is produced by press molding. In a typical process, the optical recording substrate is first press molded with a master containing the digital information to be reproduced. The thus formed information is then overcoated with a reflective layer and then with an optional protective layer. In those areas having the deformations or pits, the optical density is higher than in those areas not having the deformations.

It is desirable to produce recordable optical recording elements which, when recorded, produce a record that mimics the conventional CD on read out. Recording and read out is at about 780 nm. In this manner, information can be added to the CD and the CD can be used on a conventional CD player.

One element of this type is the so called "Photo CD". In the system in which this element is used, conventional photographic film is first processed in a conventional manner. Then, the images from the film are digitized and the digital information is recorded in a CD readable form on the optical recording element (Photo CD). Images can then be played back on a CD-type player into a conventional television. Since the element has a capacity for a number of digitized images that is greater than the number of images on a typical roll of consumer film, it is anticipated that the user will want to add images to a preexisting CD.

These recordable optical recording elements consist of a polycarbonate substrate containing a continuous tracking groove. An organic dye layer (recording layer) is solvent coated onto the grooved substrate. Fabrication is completed by coating a reflector layer, a protective layer, and a label in a fashion similar to a conventional CD digital audio disc or CD-ROM disc. In the recordable element the digital information is written into the dye layer with the focused beam of a diode laser operating in the near infrared region of the spectrum.

Commercially useful recordable optical recording elements have stringent requirements. The recording layer must have the required reflectivity and must also be able to couple with incident laser irradiation to provide features having adequate optical contrast. The layer must also have good stability towards light, heat and humidity for acceptable shelf life (incubation stability). Since the Photo CD is a consumer product, it must be capable of withstanding extreme environments. Between the time the original images are recorded on the Photo CD element and the time subsequent images are recorded, the element might be placed in strong sunlight.

In addition, the optical properties of the recording layer (its' refractive index) must be finely tuned especially as regards 'k' (the imaginary component of the index of refraction) which controls the absorption of light at the writing laser wavelength. k must be finite but low to insure a balance between coupling and reflectivity.

Experimentally, it is difficult to find a single dye with the appropriate value of k. It is common in the art to combine symmetrical cyanine dyes (usually at least two dyes, one with a high k and one with a low k) to meet the k requirements. See U.S. Patent 5,391,413. Indodicarbocyanine dyes have been used frequently. However, these dyes often have less than the desired light stability and will in fact fade to an unusable state after only a few days of intense sunlight exposure.

Optical recording layers containing metallized formazan dyes are disclosed in U.S. Patent 5,294,471. These recording layers do not have sufficient capability to couple with incident laser irradiation to form the necessary contrast and sensitivity.

U.S. Patent 5,547,728 discloses optical recording elements having recording layers comprising a mixture of metallized formazan dye and a cyanine dye. Such elements are useful but need improvements in recording sensitivity, incubation stability and light stability. Most of the expressly disclosed metallized formazans therein have a strong electron withdrawing group (typically NO_2). This results in a relatively large absorption at 780 nm. As a result, those formazans have, as part of their complex refractive index, high k values (about 0.15). This relatively large k value has a negative impact on reflectivity when used with other recording layer dyes also having high k values.

Thus, there is a continuing need for optical recording materials that have the necessary optical characteristics such that they are CD compatible, can couple with incident laser irradiation to form features with sufficient contrast and yet are light and dark (incubation) stable.

Summary Of The Invention


In accordance with the present invention there is provided an optical recording element having a transparent substrate and on the surface of said substrate, a recording layer and a light reflecting layer wherein the recording layer comprises a mixture of a metallized formazan dye and cyanine dye and the unrecorded layer is such that the real part of the refractive index (n) at 780 nm is greater than 1.8 and the imaginary part (k) is less than 0.15 wherein the metallized formazan dye has a k value of 0.00 to 0.02. For convenience the metallized formazan dyes used in this invention are sometimes referred herein as "no k" formazans.

The optical recording elements have improved incubation stability and light stability compared to prior art elements containing similar components. It was observed that the no k formazans of the invention provide increased stabilization of the composition against light fade. This results because increased concentrations of no k formazans can be used compared to formazans having a higher k. Nevertheless, reflectivity is maintained or even increased. The use of no k metallized formazans defined above allows the use of greater concentrations of metallized formazans without adversely affecting the targeted k value for the recording layer.


Detailed description of the Invention

Any cyanine dye should be useful as long as the resulting mixture has the refractive index attributes mentioned above. A particularly useful group of such dyes are indodicarbocyanine dyes. Typical indodicarbocyanine dyes include:


CD-1



CD-2




CD-7




$$k = 0.09$$

C118



$$k = 0.09$$

The no k formazans used herein are prepared according to the methods described in US 5,294,471. Exemplary no k metallized formazans fall within the scope of structure (I):



I

wherein

R_1 represents alkyl of 1-12 carbons, or alkyl substituted with one or more groups selected from the group consisting of hydroxy, acyloxy, alkoxy, aryloxy, alkylthio, arylthio, alkylsulfonyl, arylsulfonyl, thiocyno, cyano, halogen,

alkoxycarbonyl, aryloxycarbonyl, acetyl, aroyl, alkylaminocarbonyl, arylaminocarbonyl, alkylaminocarbonyloxy, arylaminocarbonyloxy, acylamino, amino, alkylamino, arylamino, carboxy, trihalomethyl, alkyl, heteroaryl, alkylureido, arylureido, succinimido and phthalimido; or aryl, or alkyl substituted aryl or alkoxy substituted aryl; and R_2 represents hydrogen, alkyl or alkoxy.

In the definitions of structure I, alkyl and alkoxy have 1-12 carbons (including cycloalkyl of 5-7 carbons), aryl, aryloxy and aroyl have 6-10 carbon atoms in an aromatic ring, and heteroaryl has 5-10 carbon atoms in an aromatic ring having at least one heteroatom. These definitions apply when the foregoing terms appear as suffixes or prefixes or alone.

In addition, each of the alkyl, cycloalkyl, aryl, heteroaryl and alkoxy groups may be further substituted with one or more groups chosen from hydroxy, acyloxy, alkoxy, aryloxy, alkylthio, arylthio, alkylsulfonyl, arylsulfonyl, thiocyno, cyano, halogen, alkoxycarbonyl, aryloxycarbonyl, acetyl, aroyl, alkylaminocarbonyl, arylaminocarbonyl, alkylaminocarbonyloxy, arylaminocarbonyloxy, acylamino, amino, alkylamino, arylamino, carboxy, trihalomethyl, alkyl, aryl, heteroaryl, alkylureido, arylureido, succinimido, phthalimido and the like.

Representative dyes falling within structure I are presented in Table 1.

















Table 1

Formazan Number	R ₁	R ₂ para subst.
NKF1		s-Butyl
NKF2		H
NKF3 k = 0.01		Methyl
NKF4		i-Propyl
NKF5 k = 0.01		Ethyl
NKF6	—CHMe_2	H
NKF7		$\text{—CH}_2\text{—N}$ 

Formazan Number	R ₁	R ₂ para subst.
NKF8		
NKF9		
NKF10		Ethyl
NKF11		i-Propyl

Optical Recording Elements

The optical elements of the invention comprise a light transmitting, typically pregrooved substrate, a dye recording layer overlaying the substrate, a light reflective layer overlaying the light absorptive layer and a protective layer overlaying the light reflective layer. The recording process will produce marks of lower reflectivity than the unmarked areas of the disk when written and read with a diode laser emitting between 770 and 800 nm. The substituents on the dye molecules are selected such that the real part of the complex refractive index (n) of the unwritten recording layer measured with a 780 nm light source is greater than 1.8 and the imaginary part (k) is less than 0.15.

The substrate may be any transparent material that satisfies the mechanical and optical requirements. The substrates are generally pregrooved with groove depths from 20 nm to 250 nm, groove widths 0.2 to 1 μ m and a pitch 0.5 to 2 μ m. The preferred material is polycarbonate, other materials are glass, polymethylmethacrylate and other suitable polymeric materials.

The preparation of the optical recording element of the invention is achieved by spin coating of the dye mixture, with or without addenda, from a suitable solvent onto a transparent substrate. For coating, the dye mixture, with or without addenda, is dissolved in a suitable solvent such that the dye is 20 or less parts by weight to 100 parts of solvent by volume. The dye recording layer of the element is then overcoated with a metal reflective layer under reduced pressure by resistive heating or a sputter method and finally overcoated with a protective resin.

Coating solvents for the dye recording layer are selected to minimize their effect on the substrate. Useful solvents include alcohols, hydrocarbon halides, cellosolves, ketones. Examples of solvents are 2,2,3,3-tetrafluoropropanol, tetrachloroethane, dichloromethane, methyl cellosolve, ethyl cellosolve, 1-methoxy-2-propanol, 4-hydroxy-4-methyl-2-pentanone. Preferred solvents are alcohols since they have the least effect on the preferred polycarbonate substrates. Mixtures containing these solvents can also be used.

Useful addenda for the recording layer include stabilizers, surfactants, binders and diluents.

The reflective layer can be any of the metals conventionally used for optical recording materials. Useful metals can be vacuum evaporated or sputtered and include gold, silver, aluminum, copper and alloys thereof.

The protective layer over the reflective layer is similarly conventional for this art. Useful materials include UV curable acrylates.

One preferred protective layer is disclosed in U.S. Patent 5,312,663. This patent discloses a two layer structure in which the layer adjacent to the reflective layer is spin coated and the second layer is screen printed.

An intermediate layer, to protect the metal layer from oxidation, can also be present.

The element of the invention can have prerecorded ROM areas as described in U.S. Patent 4,940,618. The surface of the substrate can have a separate heat deformable layer as described in U.S. Patent 4,990,388. Other patents relating to recordable CD type elements are U.S. Patent 5,009,818; 5,080,946; 5,090,009; 4,577,291; 5,075,147; and 5,079,135.

Examples of representative metallized formazans from Table 1 were combined with a cyanine dye to form optical recording layers and optical recording elements. For each of the recording layer mixtures studied, the cyanine dye to formazan ratio was varied so as to form an element capable of achieving the required refractive indices, the aim being to meet the 70% minimum reflectivity for optical data discs published in *International Standard ISO/IEC 10149*. The combined formazan cyanine dye mixture was dissolved in an appropriate solvent (typically 2,2,3,3-tetrafluoro-1-propanol (TFP)) and spun coated onto silicon wafers. Spectroscopic ellipsometric analysis of the coated wafers provided the refractive index. The film thickness corresponding to the first reflective maximum and the reflectivity at that thickness were calculated. The ratio of components was varied until the required reflectivity at 780 nm was achieved.

Measurement of a single component was made by coating the single component, such as a dye, as described above. K was determined by spectroscopic ellipsometric analysis also as described above. In some cases, a dye would crystallize preventing measurement. In the case of the metal formazans, we were able to measure k for only two dyes. Since the other dyes in this class are similar in structure to the dyes for which k measurements were obtained, and such dyes performed similarly in optical recording elements to the dyes for which k measurements were obtained, it is assumed that they have no k values (k less than 0.02) as well.

The following examples demonstrate the light and incubation stability of the optical recording layer used in the elements of this invention.

For each of the dye mixtures studied, an optical recording element was prepared by first dissolving the dye mixture in an appropriate solvent. The solvent mixture was MP/TCE [1-methoxy-2-propanol and 2,2,2-trichloroethanol (97:3)] unless otherwise stipulated. The solution was spin coated onto a 200 nm grooved polycarbonate substrate using methods well known to those skilled in the spin coating art. A complete recording element was prepared by applying 70 to 100 nm of gold to the dye film by sputtering and the gold layer was overcoated with 5 microns of a photocrosslinkable lacquer (Daicure SD-17). The element was tested by recording an EFM pattern using a commercially available media tester (MT-16 from Philips NV) and the pattern read back on a CD-CATS reader (commercially available from Audio Development Informationsteknik AB Sweden).

The light stability of the coated dye mixtures in optical recording elements was evaluated in some examples by preparing appropriate mixtures of no k formazans with a cyanine dye. The mixture was dissolved in 2,2,3,3-tetrafluoro-1-propanol at 2% solids and spun coated on 2" X 2" pieces of polycarbonate at 600 rpm. After drying, the spectra of the resulting recording layers was measured and the absorbance at the wavelength corresponding to that of maximum absorbance of CD-1 (714 nm) was recorded. The recording layers were then exposed to a 50 Klux high intensity daylight source for periods extending to 14 days, the absorbance loss (at 714 nm) noted after each increment of exposure. In control compositions containing only CD-1 (no formazan dyes) the loss was 100 percent after three days exposure.

The criteria for incubational stability, 2 weeks at 80°C/85% RH and light stability, 5 days of 50 Klux light exposure are that contrast (I11R) not drop by more than 0.05 after 2 weeks incubation, that reflectivity not drop below 65%, that symmetry not increase or decrease by more than 10 units, and that BLER not rise above 50. BLER is error rate.

Comparative example

A dye mixture containing 4 parts of CD-1 and 1 part of a prior art nickel formazan was dissolved in 1-methoxy-2-propanol. The nickel formazan has a strong electron withdrawing group. It has a structure according to structure I in which $R_1 = 3-C_7H_{15}$ and $R_2 = 4-NO_2$. The mixture was coated on a 45 nm deep grooved substrate. An optical recording element was formed therefrom and tested as described above both fresh and after 1 week incubation at 80°C/85% RH. The element of this comparative example was incubationally unstable.

Examples 1-3

Three different recording elements having recording layers formed with dye mixtures containing cyanine dye CD-1 and no k formazans NKF2, NKF3 and NKF4 at ratios of both 4 to 1 and 6 to 4 were prepared as in the comparative example. Improved light stability while maintaining the required reflectivity was noted for the 6:4 mixtures as compared to the 4:1 ratio used in the comparative example. All further examples were run at the 6:4 ratio.

Examples 4-6

Dye mixtures containing 6 parts of CD-1 and 4 parts of three different no k metallized formazans from Table 1 were

dissolved in 1-methoxy-2-propanol, coated on a 50 nm deep grooved substrate and incorporated into an optical recording element. The no k metallized formazans were NKF2, NKF4 and NKF5. The elements were tested for incubational stability for two weeks and found to be stable. These same elements were found to be stable after 5 days of light exposure.

Examples 7-9


Examples 4-6 were repeated using no k formazans NKF1, NKF3 and NKF6. Light and incubational stability similar to that observed in examples 4-6 were noted.

This invention has been described with particular reference to preferred embodiments thereof but it will be understood that modifications can be made within the spirit and scope of the invention.

Claims

1. An optical recording element having a transparent substrate and on the surface of said substrate, a recording layer and a light reflecting layer wherein the recording layer comprises a mixture of a metallized formazan dye and cyanine dye and the unrecorded layer is such that the real part of the refractive (n) at 780 nm is greater than 1.8 and the imaginary part (k) is less than 0.15 wherein the metallized formazan dye has a k value of 0.00 to 0.02.

2. The optical element of claim 1 wherein the metallized formazan dye has the structure I as follows:



I

wherein

R_1 represents alkyl of 1-12 carbons, or alkyl substituted with one or more groups selected from the group consisting of hydroxy, acyloxy, alkoxy, aryloxy, alkylthio, arylthio, alkylsulfonyl, arylsulfonyl, thiocyno, cyano, halogen, alkoxy carbonyl, aryloxy carbonyl, acetyl, aroyl, alkylaminocarbonyl, arylaminocarbonyl, alkylaminocarbonyloxy, arylaminocarbonyloxy, acylamino, amino, alkylamino, arylamino, carboxy, trihalomethyl, alkyl, heteroaryl, alkylureido, arylureido, succinimido and phthalimido; or aryl, or alkyl substituted aryl or alkoxy substituted aryl; and


R_2 represents hydrogen, alkyl or alkoxy.

3. The element of claim 2 wherein










R_1 represents phenyl, methyl phenyl, ethoxyphenyl and i-propyl; and

R_2 represents hydrogen, methyl, ethyl, i-propyl, n-butyl, s-butyl or morpholinomethyl.




4. The element of claim 3 wherein the metallized formazan is selected from Table 1:

**Table 1**


Formazan Number	R ₁	R ₂ para subst.
NKF1		s-Butyl
NKF2		H
NKF3 k = 0.01		Methyl
NKF4		i-Propyl

Formazan Number	R ₁	R ₂ para subst.
NKF5 k = 0.01		Ethyl
NKF6	—CHMe ₂	H
NKF7		—CH ₂ —N— 
NKF8		—CH ₂ —N— 
NKF9		—CH ₂ —N— 
NKF10		Ethyl
NKF11		i-Propyl


5. The formazan of claim 3 selected from formazans numbers NKF1, NKF2, NKF3, NKF4, NKF5, NKF6 and NKF11 of Table 1.
6. An element according to any one of the preceding claims wherein the cyanine dye is an indodicarbocyanine dye.
7. An element according to any one of claims claim 1-5 wherein the cyanine dyes are selected from the group consisting of



and



8. The element of any one of claims 1-5 wherein the cyanine dye has the structure



9. The element of claim 8 wherein the cyanine dye to metallized formazan dye ratio is 6:4.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 20 3048

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 729 139 A (TDK CORP) * page 11: examples I-16,17 * * page 14 - page 15; examples I-43,47,49 * * page 16: examples I-52,57 * * page 18: examples I-67 * * page 19: examples I-83 * * page 52 - page 53; examples 15,16 * * claims 1,8,9 *	1-3,6-9	G11B7/24 C09B67/00 C09B50/00
D,X	US 5 547 728 A (CUNNINGHAM MICHAEL P ET AL) * column 11 - column 14; claims 1-10; examples 1-10 *	1-3,6-9	
D,A	US 5 294 471 A (EVANS STEVEN ET AL) * claims 1-17 *	1-9	
P,A	EP 0 750 019 A (EASTMAN KODAK CO) * claim 1 *	1-9	
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			G11B C09B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 28 January 1998	Examiner Vogt, C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (P4/C01)